

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-319575

(43)Date of publication of application : 03.12.1996

(51)Int.Cl.

C23C 18/31
C01G 55/00
C23C 18/18

(21)Application number : 07-126544

(71)Applicant : FUJI SEIKO HONSHA:KK

(22)Date of filing : 25.05.1995

(72)Inventor : TAKEDA KIYOHARU
MIYAKE MIKIO

(54) METHOD FOR METAL-PLATING CARBON FINE GRAIN

(57)Abstract:

PURPOSE: To form a uniform metallic film on the surface of carbon fine grains.

CONSTITUTION: Carbon fine grains constituted of mesophase spherulites are subjected to oxidation treatment, are deposited with Pd (NH₃)₄Cl₂ by impregnation and are applied with electroless plating. By the oxidation treatment, acidic functional groups are introduced into the surface of the spherulites, Pd is deposited over the acidic functional groups, and by the electroless plating, a uniform metallic film can be formed via Pd.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]